

## PHILLYSTRAN® LARGE DIAMETER OFFSHORE ROPES TECHNORA® (ARAMID)

195-2/06

Phillystran PST large diameter Technora® fiber ropes are manufactured in a 7x19 wire lay construction. These ropes are especially designed for high strength and lightweight applications such as mooring lines and deep water buoy anchor lines. All PST ropes have a heavy duty braided polyester jacket for increased abrasion resistance. Other jackets, including extruded jackets, are available upon request.



PART NUMBER	BREAK STRENGTH		DIAMETER		WEIGHT	
	LBS	kN	IN	mm	LBS/1000 FT	kg/km
PST 1000	1,180,000	5,250	3-5/8	92	4,000	5,950
PST 1250	1,250,000	5,560	3-7/8	98	4,300	6,400
PST 1500	1,500,000	6,670	4-1/4	108	5,200	7,740
PST 1750	1,750,000	7,780	4-1/2	114	6,000	8,930
PST 2000	2,000,000	8,900	5	127	7,000	10,400
PST 2250	2,250,000	10,000	5-1/4	133	7,900	11,800
PST 2500	2,500,000	11,100	5-5/8	143	9,000	13,400
PST 2750	2,750,000	12,200	5-7/8	149	9,700	14,400
PST 3000	3,000,000	13,300	6-1/8	156	10,700	15,900

Weights & Dimensions can vary  
TECHNORA® is a Registered Trademark of Teijin, Ltd.

**CAUTION: Break Strength:** The breaking strength of a rope is the load at which a new rope will break when tested under laboratory conditions. Break strength should not be mistaken for safe working load. **Safe Working Load:** Because of the wide range of rope use, rope condition and the degree of risk of life or property, it is not possible to make a blanket recommendation for safe working load. It is ultimately dependent on the rope user to determine what percentage of break strength is their own safe working load. **Wear:** Ropes wear out with use; the more severe the usage, the greater the wear. It is often not possible to detect wear on a rope by visible signs alone. Therefore, it is recommended that the rope user determine a retirement criteria for ropes in their application. For assistance in developing safe working load and retirement criteria for each application please call or write Phillystran, Inc.

All printed statements, data and recommendations are based on reliable information and tests, and are presented without any guarantee or warranty. Statements regarding the use of Phillystran, Inc.'s products and processes are not to be construed as recommendations for use in violation of any applicable laws, regulations or patent rights. © All rights reserved.

**Phillystran, Inc.**  
151 Commerce Drive  
Montgomeryville, PA 18936-9628 USA

Phone: 215-368-6611  
Fax: 215-362-7956  
E-mail: [info@phillystran.com](mailto:info@phillystran.com)